

PG-T

Technical Datasheet



Core values, quality products

Description

PG-T is a high quality graphite laminate material in which exfoliated graphite is mechanically bonded to a 316 stainless steel tanged insert

Application

PG-T has excellent mechanical strength, outstanding stress retention properties, and is chemically resistant to most fluids. It is capable of sealing a wide temperature range, and is used throughout industry for sealing steam, hydrocarbons and many chemicals.


Typical Physical Properties

Thickness		1.5mm
Density		1.0g/cc
Insert Thickness		0.1mm
Compression	ASTM F36J	30% to 37%
Recovery	ASTM F36J	20%
Residual Stress	BS7531 (40N/mm ² @ 300°C)	37 MPa
Gas leakage	BS7531	<1.0 ml/min
Ash Content		1.0% max
Chloride Content		45 ppm max
Sulphur Content		1200 ppm max



Availability

Thickness	1.0mm to 3.0mm
Sheet size	1500mm x 1500mm, 1000mm x 1000mm
Insert	316 as standard,. Other materials available on request
Colour	Black



- A = Suitable subject to chemical compatibility
- B = Please contact our Technical Team
- C = Not Suitable

As the company's products are used in multiple applications and as the company has no control over the method of their use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise. Any technical co-operation is given for customers assistance only and without liability on the part of the company.

Disclaimer: The information within this document is believed to be correct at the time of publication; however, the document is for guideline use only. For complete accuracy, always check the product with an SBS representative. Missing information was either not available or disclosed. It is your responsibility that any product meets the necessary requirements. Any reliance placed upon this information will be totally at the user's risk.